

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

TECHNICAL DATA FOR EUREKA 726 ELECTRODE

Dated: March 31, 1995

Revised: July 8, 2013

INTRODUCTION

Eureka 726 Electrode is a smooth running basic coated stick electrode with a modified H-12 hot working tool steel alloy. The electrodes are designed for superior weldability having no spatter, a stable arc, good wet out, and easy slag removal.

METALLURGICAL CHARACTERISTICS

Eureka 726 Electrodes are a highly modified A.I.S.I. type H-12 hot work tool steel that have an as welded hardness of 55 - 60 HRC. The weld deposits are very resistant to wear and resist softening at elevated temperatures.

RECOMMENDED APPLICATIONS

Eureka 726 Electrodes is used on hot punches and trim dies, hot extrusion dies, hot press forging dies and forging die inserts. It is used in areas where severe heat and abrasion will be encountered. Some forged dies would be hand tools, gears, discs and connecting rods. This alloy performs well in shallow impressions and is often use as an overlay or hard facing alloy.

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

WELDING PARAMETERS

SIZE		AMPERAGE RANGE
3/32"	2.4mm	70 – 120
1/8"	3.2mm	100 – 140
5/32"	4.0mm	140 – 170
3/16"	4.8mm	170 – 225
1/4"	6.35mm	225 – 300
5/16"	7.94mm	300 – 375
3/8"	9.5mm	350 – 425

TYPICAL CHEMISTRY

C	Mn	Si	Cr	Mo	W	V
.30	.70	.50	5.5	2.5	3.0	.50

PHYSICAL AND OR MECHANICAL PROPERTIES

AS WELDED HARDNESS

50-55 HRC

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

TEMPERING DATA

The tempering data is to be used as a guide. Your results may differ due to the many variables in the utilization of this product.

SINGLE TEMPER CURVE EUREKA 726

