

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

TECHNICAL DATA FOR EUREKA N2 ELECTRODE

Dated: March 31, 1995

Revised: July 8, 2013

INTRODUCTION

Eureka N2 Electrode is a smooth running basic coated stick electrode that is a low alloy filler metal. The electrodes are designed for superior weldability having no spatter, a stable arc, good wet out, and easy slag removal.

METALLURGICAL CHARACTERISTICS

Eureka N2 Electrode is a carefully balanced Molybdenum, Manganese and Nickel alloy that has an as welded hardness of 18-23HRC. This alloy displays high impact resistance and moderate abrasion resistance. The microstructure of ferrite and bainite promotes high crack resistivity.

RECOMMENDED APPLICATIONS

Eureka N2 Electrodes is an excellent choice for welding forging components such as rams, sow blocks, die holders, die shanks, hammers bases and columns. It is also utilized in steel mills and in maintenance shops for welding general machine parts such as steel gears, large arbors and shafts.

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

WELDING PARAMETERS

SIZE	AMPERAGE RANGE
3/32" 2.4mm	70 – 120
1/8" 3.2mm	100 – 140
5/32" 4.0mm	140 – 170
3/16" 4.8mm	170 – 225
1/4" 6.35mm	225 – 300
5/16" 7.94mm	300 – 375
3/8" 9.5mm	350 – 425

TYPICAL CHEMISTRY

C	Mn	Si	Mo	Ni
.08	.55	.55	.60	3.0

PHYSICAL AND OR MECHANICAL PROPERTIES

TENSILE STRENGTH 157,000 psi

ELONGATION 17%

CHARPY "V" NOTCH 42 Ft/lbs.

AS WELDED HARDNESS

18-23 HRC

Eureka Welding Alloys

2000 E. Avis Drive


Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

TEMPERING DATA

The tempering data is to be used as a guide. Your results may differ due to the many variables in the utilization of this product.



Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

