

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

TECHNICAL DATA FOR EUREKA N3 ROBOWELD METAL CORED WIRE

Dated: January 27, 2015

Revised:

INTRODUCTION

Eureka RoboWeld N3 Metal Cored Wire was specifically developed for robotic welding of forging dies of most any designs. The RoboWeld wires when used with the **NEWELD** robotic process do not require peening of weld metal due to lower welding stresses. This is accomplished through a combination of five factors;

- 1) High quality wires utilizing the very best raw materials available.
- 2) The programmed pulse arc welding energy has lower penetration, dilution, and heat input.
- 3) The programmed robot maintains precise torch angles, stick out length and travel speeds.
- 4) Programed arc start up and arc ending amperages and voltages are ramped up and down.
- 5) Only a few layers of weld metal are required to achieve nearly pure weld metal.

Eureka RoboWeld N3 Metal Cored Wire is a medium alloy filler metal. The wire has a smooth spray transfer arc with nearly no slag to contend with. The wire is formulated to develop high quality weld deposits that are defect free. The wire is designed for multi-pass welding which greatly increases productivity.

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

METALLURGICAL CHARACTERISTICS

Eureka RoboWeld N3 Metal Cored Wire is a carefully balanced Molybdenum, Manganese and Nickel alloy that has an as welded hardness of 29-34HRC and tempers up to 35-40HRC. This alloy displays high impact resistance and moderate abrasion resistance. The microstructure of ferrite and bainite promotes high crack resistivity.

RECOMMENDED APPLICATIONS

Eureka RoboWeld N3 Metal Cored Wire is often used for the welding of forging dies when repairing standard die block metal in 32-42HRC range. It exhibits good wear characteristics and much greater crack resistance when compared to standard die block metal. It is utilized as an underlay alloy for crack sensitive areas in the bottom of impressions. It is also utilized in the repair of shanks and components such as rams, sow blocks and die holders where increased hardness and strength is required over that of the Eureka N-2 and Eureka 625.

WELDING PARAMETERS

TYPE	SIZE	AMPERAGE	VOLTS
Metal Cored Wire	1/16" 1.6mm	180 – 350	24 – 31

**Use DC Current with a Stick Out of
1/2" - 3/4" (12mm-19mm)**

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

RECOMMENDED SHIELDING GASES

90% Argon, 10% Co2

92% Argon, 8% Co2

GAS FLOW RATE

1/16" 1.6mm 40-80 CFH

PHYSICAL AND OR MECHANICAL PROPERTIES

AS WELDED HARDNESS

29-34 HRC

Eureka Welding Alloys

2000 E. Avis Drive

Madison Heights, MI 48071

Phone: 248-588-0001 Fax: 248-585-7711 Toll Free: 800-962-8560

E-mail: info@eurekaweldingalloys.com Website: www.eurekaweldingalloys.com

TEMPERING DATA

The tempering data is to be used as a guide. Your results may differ due to the many variables in the utilization of this product.

